



EL030 – ANTICORROSIVE PRIMER



Ready for use



Film thickness:
5-10 μ



Air drying at 20° C:
30-40 min.

DESCRIPTION

Grey one component anticorrosive primer, ready for use in an aerosol.

USE

Special product used in Car and Industrial Refinish as anticorrosive primer and adhesion coat on metal for the carrying out of small repairs (FAST REPAIRS). In General Industry as protection primer of metal substrates.

CHARACTERISTICS

- Easy to use ready for use (aerosol)
- Quick drying
- Good anticorrosive protection
- Good adhesion to steel, aluminium and relevant alloys, electro zinc-coated and hot zinc-coated steel

SUBSTRATE PREPARATION

Degrease carefully with 00695 SOLVENTE ANTISILICONE SLOW and sand with fine grit paper.
For further information about the product's use in FAST REPAIRS cycles see Data Sheets Cycles N° 005 and N° 006.

APPLICATION

Spraying.

Ready for use. Shake well 2-3 minutes before use.

Spray temperature: 15-30° C

N° of coats: 1-2

Spray distance: 20-25 cm

Flash-off: 5 minutes at 20°C

Recommended film thickness: 5-10 μ

DRYING TIMES

Air drying at 20°C

Dust-free: 10 minutes

Tack-free: 15-20 minutes

Through-drying: 24 hours



SUGGESTED OVERCOATINGS

Fillers and top coats of the Lechler range can be overcoated without sanding after 30-40' flash-off at 20°C. For further information about the product's use in FAST REPAIRS cycles see Data Sheets Cycles N° 005 and N° 006.

ATTENTION: After use turn the aerosol upside down and spray the rest out of the supplying pipe in order to avoid blockage problems during the storage time before the following use.

SHELF LIFE AT 20°C: 24 months

DATA SHEET N. 0499-GB
UP DATED 09/2003

The information shown in these sheets is given in good faith as being true and although every effort of verification has been made before use, we cannot accept responsibility for any inaccuracy.

THIS PRODUCT IS FOR THE PROFESSIONAL PAINTING OF ROAD VEHICLES BY QUALIFIED PERSONNEL.